



Advanced XP 2K is a water-based, two-component floor finish remarkable for its extremely high resistance to black heel marks, scratches and stains. Its superior performance is perfectly suited for high traffic, commercial areas, as its extreme protection and resistance make the floors easy to clean and maintain. The wood is left with a rich and full appearance, due to the high solids content.

- **High commercial traffic**
- **Meets the highest standards for slip resistance**
- **Superior performance**
- **Indoor climate labeled**
- **Available in matte, satin & semi gloss**



AppArea

For finishing new, untreated and newly-sanded wood floors in public areas with high traffic. Ideal for all types of wood.

Work_Descrip_Label

Preparation_Label It is important that both wood and floor finish have a temperature of min. 59°F (preferably around 68°F) and air humidity of approx. 50%. Make sure that the room is well-ventilated for optimal evaporation and drying time. For the final sanding to bare wood, use grit 100-120 sandpaper or sanding pad. Vacuum thoroughly and tack the floor afterwards, using a tightly-wrung water-soaked mop/cloth. The floor must be completely dry before sealing. When sealing, use WOCA Sealers for newly sanded wood to reduce side bonding.

Always remember to test on a less visible spot to check the compatibility of the surface with the product.

FinalSanding Grit 100-120

Treatment 1 x sealer + 2 x Advanced XP 2K

ApplicationDay1 Apply the sealer if not using a stain. When dry, mix WOCA Advanced Hardener with the floor finish and shake thoroughly before use. Leave the mixture to stand for ten minutes before use, to allow the hardener to activate. A coat of Advanced XP 2K floor finish should be applied undiluted, using a brush or roller. Avoid puddles of floor finish. Apply the floor finish wet into wet, to avoid overlaps. Leave the surface to dry until next day.

ApplicationDay2 Sand the surface with grit 120-200 and vacuum clean the surface thoroughly. Apply the final coat of Advanced XP 2K floor finish with hardener (freshly mixed). If the final coat of floor finish is applied after more than 24 hours of drying time, a washing down with WOCA Intensive Wood Cleaner and an intermediate sanding should always be conducted.

NoteTxt Water and coloured fluids, such as red wine and coffee, must be wiped off immediately to prevent staining.

DryingTime

DryBetweenCoat 2-3 hours at 68°F.

DryLightUse 5-6 hours.



Techdata_label

Density	1.02 to 1.06 g/cm ³
PHVvalue	7.5 to 8.5
ShelfLife	2 years from manufacturing date
AppTemp	+59-77°F. and approx. 50% air humidity.
Viscosity	Approx. 22 sec.
Consumption	Approx. 85-110 sq.ft./L, depending on wood type and surface.
MixingRatio	500 ml hardener to 4,5 L floor finish.
PotLife	The mixture must be used within 5 hours.
CleaningTools	Use water.
Storage	+50-77°F. Keep out of reach of children. Do not expose to heat (e.g. sunlight). Store frost-free during winter and cool during summer (max. +77°F).
AvailPotSizes	4.5 L
Authorisations	Indoor climate labeled, R10 AgBB Z-157.10-182

MaintenanceProd

WeeklyCleanProd	Vinyl and Finish Cleaner
HalfYearlyCare	Vinyl and Finish Care
RelatedProducts	Intensive Wood Cleaner
ApplicationTool	Brush or microfiber roller, 3/8" mm pile.

Contact_Label

WOCA Denmark A/S
Tvæervej 6
DK - 6640 Lunderskov
T +45 9958 5600
info@wocadenmark.com
wocadenmark.com

Disclaimer_Long