



Advanced XP 2K is a water-based, two-component floor finish remarkable for its extremely high resistance to black heel marks, scratches and stains. Its superior performance is perfectly suited for high traffic, commercial areas, as its extreme protection and resistance make the floors easy to clean and maintain. The wood is left with a rich and full appearance, due to the high solids content.

- **High commercial traffic**
- **Meets the highest standards for slip resistance**
- **Superior performance**
- **Indoor climate labeled**
- **Available in matte, satin & semi gloss**



## AppArea

For finishing new, untreated and newly-sanded wood floors in public areas with high traffic. Ideal for all types of wood.

## Work\_Descrip\_Label

|                   |  |
|-------------------|--|
| Preparation_Label | <p>It is important that both wood and floor finish have a temperature of min. 59°F (preferably around 68°F) and air humidity of approx. 50%. Make sure that the room is well-ventilated for optimal evaporation and drying time. For the final sanding to bare wood, use grit 100-120 sandpaper or sanding pad. Vacuum thoroughly and tack the floor afterwards, using a tightly-wrung water-soaked mop/cloth. The floor must be completely dry before sealing. When sealing, use WOCA Sealers for newly sanded wood to reduce side bonding.</p> <p>Always remember to test on a less visible spot to check the compatibility of the surface with the product.</p> |
| Treatment         | 1 x sealer + 2 x Advanced XP 2K  |
| ApplicationDay1   | Apply the sealer if not using a stain. When dry, mix WOCA Advanced Hardener with the floor finish and shake thoroughly before use. Leave the mixture to stand for ten minutes before use, to allow the hardener to activate. A coat of Advanced XP 2K floor finish should be applied undiluted, using a brush or roller. Avoid puddles of floor finish. Apply the floor finish wet into wet, to avoid overlaps. Leave the surface to dry until next day.   |
| ApplicationDay2   | Sand the surface with grit 120-200 and vacuum clean the surface thoroughly. Apply the final coat of Advanced XP 2K floor finish with hardener (freshly mixed). If the final coat of floor finish is applied after more than 24 hours of drying time, a washing down with WOCA Intensive Wood Cleaner and an intermediate sanding should always be conducted.   |
| NoteTxt           | Water and coloured fluids, such as red wine and coffee, must be wiped off immediately to prevent staining.   |

## DryingTime

|                |                   |
|----------------|-------------------|
| DryBetweenCoat | 2-3 hours at 68°F |
| DryLightUse    | 4-6 hours at 68°F |
| FullyHard      | 5 days at 68°F    |



### Techdata\_label

---

|               |  |
|---------------|--|
| ShelfLife     | 2 years  |
| AppTemp       | +59-77°F and approx. 50% air humidity.   |
| Viscosity     | 20-25 Sec. DIN Cup 4   |
| Consumption   | 85-110 sq.ft./L  |
| Colours       | Colorless - Satin, Colorless - Semi-gloss  |
| MixingRatio   | 10% or 500 ml to 5 L lacquer   |
| PotLife       | 3pot   |
| CleaningTools | Use water  |
| Storage       | +50-77°F. Keep out of reach of children. Do not expose to heat (e.g. sunlight). Store frost-free during winter and cool during summer. |
| AvailPotSizes | 5  |

### MaintenanceProd

---

|                 |                          |
|-----------------|--------------------------|
| WeeklyCleanProd | Vinyl and Finish Cleaner |
| HalfYearlyCare  | Vinyl and Finish Care    |
| RelatedProducts | Intensive Wood Cleaner   |

### Contact\_Label

---

WOCA Denmark A/S  
Tvæervej 6  
DK - 6640 Lunderskov  
T +45 9958 5600  
info@wocadenmark.com  
wocadenmark.com

*This information is based on extensive laboratory testing and practical experience. Because the conditions under which the product is used are often beyond the control of WOCA Denmark, we can only guarantee the quality of the actual product. WOCA Denmark A/S accepts no liability for incorrect use and handling of the product. In principle, this product can be considered an intermediate product, as results depend on construction, the nature of the surface, pretreatment, temperature, air humidity, application etc. WOCA Denmark A/S reserves the right to change the product and the stated information without notice. This label/product description replaces all previous versions.*