



Master Filler Aqua is a water-based, thick and easy-to-sand gap filler for joints, holes and cracks in wooden parquet floors in e.g. brick or herringbone patterns. The filler produces a uniform finish, is extremely easy to work with and will not crack as it is elastic and allows the wood to work.

- **Easy to sand once it has cured**
- **Water-based**
- **Thick, elastic consistency**
- **Odour neutral**



## Application area

For filling new, untreated, newly-sanded and previously treated wooden surfaces. Ideal for all species of wood, except merbau.

## Work description

Preparation	<p>It is important that both wood and filler have a temperature of min. 15 °C (preferably around 20 °C) and air humidity of approx. 50%. Make sure that the room is well-ventilated for optimal evaporation and drying time. The surface must be completely clean, dry and free of dirt, wax, grease, polish, etc. Grime and irregularities should be removed using a sanding machine. If necessary, clean the surface using WOCA Intensive Wood Cleaner, diluted 1:20, before sanding.</p> <p>Always remember to test on a less visible spot to check the compatibility of the surface with the product.</p>
Final sanding	Grit 60-80.
Treatment	<p>Shake the container well before use. Mix the Master Filler Aqua and the sanding residue into a nice and soft paste. The structure of the filler can be adjusted using the fine or coarse sanding residue. Distribute the filler evenly, using a stainless steel applicator. Remove as much excess filler as possible before it begins to cure. Repeat the process for larger joints, holes and cracks if required. Sand the surface with grit 100-120 sandpaper once the surface is dry. The surface can then be lacquered using one of WOCA's lacquers, following the product instructions.</p>
Please note	<p>Be aware of compatibility issues for woods with high tannic acid levels, or for merbau and exotic wood species. Master Filler Aqua must not be diluted.</p>

## Drying time

Drying time	30-60 minutes at 20°C
Recommendation	<p>Optimal joint width is 3-4 mm. Drying time may vary depending on the size of the crack, the temperature and ventilation. For larger joints, Master Filler Aqua should be left to dry completely before further treatment</p>



Master Filler Aqua

**Water-based gap filler for wooden floors**

Technical Data Sheet

29.01.2022 - p. 2/2

## Technical data

Shelf life	1 year
Application Temperature	10-25
Viscosity	35-40 Sec. DIN Cup 4
Coverage	15-20 m <sup>2</sup> /L
Colours	Colourless
Mixing ratio	Mix 20% sanding residue, depending on the colour of the wood and the depth/width of the join.
Cleaning of tools	Use soap and water
Storage	+10-25°C. Keep out of reach of children. Do not expose to heat (e.g. sunlight). Store frost-free during winter and cool during summer.
VOC	VOC-Max: <2,5 g/l, MAXIMUM VOC CONTENT [A/e (WB)]: 130 g/l.
Packaging	5 liters

## Maintenance and related products

Related products	Intensive Wood Cleaner, #551525 Master Base Primer, #690151A/52A Master Classic Lacquer, #690115A/16A/17A Master Vista Lacquer, #690120A/21A/22A Master Optima Lacquer, #690125A/26A/27A/28A Master QP Lacquer, #690130A/31A Master TS-2K Lacquer, #690136A/37A Master XP-2K Lacquer, #690145A/46A/47A Master RD-2K Lacquer, #690140A/41A
------------------	---

## Contact

WOCA Denmark A/S  
Tvæervej 6  
DK - 6640 Lunderskov  
T +45 9958 5600  
info@wocadenmark.com  
wocadenmark.com

*This information is based on extensive laboratory testing and practical experience. Because the conditions under which the product is used are often beyond the control of WOCA Denmark, we can only guarantee the quality of the actual product. WOCA Denmark A/S accepts no liability for incorrect use and handling of the product. In principle, this product can be considered an intermediate product, as results depend on construction, the nature of the surface, pretreatment, temperature, air humidity, application etc. WOCA Denmark A/S reserves the right to change the product and the stated information without notice. This label/product description replaces all previous versions.*