

Use Maintenance Oil Diamond Active for the ultimate care and maintenance of your oiled wood floor. This exclusive, low-odour, extremely tough maintenance oil is made from the absolute highest quality raw materials, to benefit both you and your oiled floor. In addition to being very easy to use and assuring minimal product waste, the maintenance oil refreshes the natural, warm glow of the wood and increases resistance to stains, via a unique hyper cross linking technology. Maintenance Oil Diamond Active is suitable for both manual and machine application to oiled floors.

- **Resistant to liquids such as water, coffee, tea and red wine**
- **Resistant to scratches and marks**
- **Gives the wood a beautiful, breathable surface**
- **IBR-certified**



AppArea

For oiled surfaces

Work_Descrip_Label

Preparation_Label	<p>It is important that the product, the room and the floor are at a temperature between 15 °C and 30 °C and that air humidity is approx. 50 %. Wood humidity must not exceed 12 %. Make sure that the room is well-ventilated for optimal evaporation and drying time.</p> <p>The surface must be free of grime, grease and wax. Wash the floor with WOCA Intensive Wood Cleaner and leave the floor to dry for a least 8 hours or until it is completely dry.</p> <p>Always remember to test on a less visible spot to check the compatibility of the surface with the product.</p>
Treatment	<p>Thoroughly shake the container of Maintenance Oil Diamond Active, both before and during use. Apply approx. 1 dl oil per 4 m² floor using a pad, short-bristled paint roller (3-4 mm) or a buffing machine with a white or beige pad on slightly larger areas. Make sure that the oil is rubbed well into the wood. Continue polishing until the wood seems saturated and the surface has an even, uniform appearance. Remove excess oil with clean, lint-free cotton cloths, before proceeding to the next section. The surface should not appear wet and no excess oil should remain on the surface. Continue, following the aforementioned method until the whole floor has been treated.</p> <p>If the floor is polished with a buffing machine, it can be used with caution after 4 hours of drying time at 20°C. If polished manually, the floor can be used with caution after approximately 24 hours.</p>
NoteTxt	<p>Do not expose the floor to water or clean it for the first 3 days, while the oil is hardening.</p>

DryingTime

DryMachinePolis	3-4 hours at 68°F
DryManualPolish	24 hours at 68°F
FullyHard	3 days at 68°F
Rec	Do not expose the floor to water or clean it for the first 48 hours, while the oil is hardening.



Techdata_label

Density	0.90-0.95 g/ml.
SolidContent	70-75%
ShelfLife	36M
AppTemp	+59-77°F and approx. 50% air humidity.
Consumption	430-540 sq.ft./L
CleaningTools	Use WOCA Solvent or turpentine
Storage	+50-77°F. Keep out of reach of children. Do not expose to heat (e.g. sunlight). Store frost-free during winter and cool during summer.
AvailPotSizes	2.5

MaintenanceProd

Contact_Label

WOCA Denmark A/S
Tvæervej 6
DK - 6640 Lunderskov
T +45 9958 5600
info@wocadenmark.com
wocadenmark.com

This information is based on extensive laboratory testing and practical experience. Because the conditions under which the product is used are often beyond the control of WOCA Denmark, we can only guarantee the quality of the actual product. WOCA Denmark A/S accepts no liability for incorrect use and handling of the product. In principle, this product can be considered an intermediate product, as results depend on construction, the nature of the surface, pretreatment, temperature, air humidity, application etc. WOCA Denmark A/S reserves the right to change the product and the stated information without notice. This label/product description replaces all previous versions.