

Worktop Oil is an air-hardening oil that penetrates deep into the wood, leaving a tough water- and stain-resistant surface. The oil highlights the wood's natural glow and gives the surface a natural, fresh appearance. Worktop Oil can be used on surfaces that are untreated or that have previously been oil-treated/sanded.

- **Provides a dirt and water-resistant surface**
- **Natural appearance**
- **Can be used on all wood varieties**
- **Highlights the glow and grain structure of the wood**
- **Safe for food contact**



AppArea

For the care and maintenance of untreated or previously oil-treated/sanded surfaces. Only for indoor use.

Work_Descrip_Label

Preparation_Label	It is important that both wood and oil have a temperature of min. 15°C (preferably around 20°C) and air humidity of approx. 50 %. Make sure that the room is well-ventilated for optimal evaporation and drying time. Sand old and previously treated surfaces with grit 180 sandpaper. Vacuum clean the surface thoroughly. Thoroughly clean the surface with Intensive Wood Cleaner, mixed 1 part cleaner to 20 parts water. Then wash with clean water. After cleaning, leave the surface to dry for at least 8 hours at 20°C. Mix the oil thoroughly.
FinalSanding	g180
Treatment	Use a paintbrush to distribute an appropriate amount of oil in an even, covering coat. If possible, the reverse side of the work surface should also be given a coat of oil. Wait approx. 30 minutes at 20°C, while the oil soaks into the wood. Apply more oil if dry areas appear. Polish with a red or white WOCA hand scrubber along the direction of the wood grain. This will make the surface more durable. Then wipe off all excess oil with a lint-free cotton cloth. No excess oil should remain on the surface. If the surface is not wiped sufficiently dry, it will dry with a sticky texture. Allow the surface to rest for an hour and repeat steps. The surface should be treated two or three times before use. For the final treatment, sand in wet oil with grit 280-400 wet sandpaper, before wiping off with a lint-free cotton cloth.
NoteTxt	The worktop should be maintained at least once a year, or when necessary. For a superior result, use Worktop Oil or WOCA Maintenance Gel. For a more thorough restoration, follow the entire procedure.

DryingTime

DryingTime	8-10 hours at 68°F
DryLightUse	24 hours at 68°F
FullyHard	7 days at 68°F



Techdata_label

Density	0.90-0.95 g/ml.
SolidContent	70-75%
ShelfLife	36M
Viscosity	30-35 Sec. DIN Cup 4
Consumption	130-160 sq.ft./L
CleaningTools	Use turpentine
AvailPotSizes	.75

MaintenanceProd

Contact_Label

WOCA Denmark A/S
Tvæervej 6
DK - 6640 Lunderskov
T +45 9958 5600
info@wocadenmark.com
wocadenmark.com

This information is based on extensive laboratory testing and practical experience. Because the conditions under which the product is used are often beyond the control of WOCA Denmark, we can only guarantee the quality of the actual product. WOCA Denmark A/S accepts no liability for incorrect use and handling of the product. In principle, this product can be considered an intermediate product, as results depend on construction, the nature of the surface, pretreatment, temperature, air humidity, application etc. WOCA Denmark A/S reserves the right to change the product and the stated information without notice. This label/product description replaces all previous versions.